



## Technical Data Sheet

GLOBALPRENE 3537 Styrene-Butadiene block copolymer				
<b>Features:</b>		<b>Typical Application:</b>		
Linear block copolymer High diblock		Asphalt modification, compounding Solvent-based adhesives		
Typical Properties	Unit	Typical Value	Range	Test Method
Specific Gravity	g/cc	0.94	N/A	ASTM D 792
Volatile Matter	%	0.21	1.0 max	ASTM D 5668
Ash Content	%	0.1	1.0 max	ASTM D 5667
Bound Styrene	%	30	32 - 38	-
Coupling Efficiency	%	90	58 - 72	ASTM D 5296

Packaging: 30 lb bag, 900 lb super sack, 800 lb box

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)