



## Product Information

### VESTAMID® HT*plus* M1035

#### Glass-fiber reinforced polyphthalamide compound for injection molding

VESTAMID HT*plus* M1035 is a glass-fiber reinforced (50%), heat-stabilized polyphthalamide compound (PPA) for injection molding.

This compound is especially suitable for manufacturing parts subjected to high temperature.

VESTAMID HT*plus* M1035 is supplied as cylindrical pellets in polyethylene packaging.

Drying at 120°C for at least 4 hours before processing is recommended.

Property	Test method		Unit	VESTAMID HTplus M1035	
	international	national			
Density	23°C	ISO 1183	DIN EN ISO 1183	g/cm <sup>3</sup>	1.64
Tensile test		ISO 527-1	DIN EN ISO 527-1		
Stress at break		ISO 527-2	DIN EN ISO 527-2	MPa	250
Strain at break				%	2
Tensile modulus		ISO 527-1	DIN EN ISO 527-1	MPa	19000
		ISO 527-2	DIN EN ISO 527-2		
Flexural test		ISO 178	DIN EN ISO 178		
Flexural strength				MPa	360
Flexural modulus		ISO 178	DIN EN ISO 178	MPa	16000
CHARPY impact strength		ISO 179/1eU	DIN EN ISO 179/1eU		
	23°C			kJ/m <sup>2</sup>	65 C <sup>1)</sup>
	-40°C			kJ/m <sup>2</sup>	50 C <sup>1)</sup>
CHARPY notched impact strength		ISO 179/1eA	DIN EN ISO 179/1eA		
	23°C			kJ/m <sup>2</sup>	12 C <sup>1)</sup>
	-40°C			kJ/m <sup>2</sup>	14 C <sup>1)</sup>
Vicat softening temperature		ISO 306	DIN EN ISO 306		
Method A	10 N			°C	313
Method B	50 N			°C	289
Linear thermal expansion		ISO 11359	DIN 53752		
	20°C				
longitudinal				10 <sup>-5</sup> K <sup>-1</sup>	2.74
transverse				10 <sup>-5</sup> K <sup>-1</sup>	2.29
Volume resistivity		IEC 60093	IEC 60093	Ohm · m	10 <sup>15</sup>
Spec. surface resistance		IEC 60093	IEC 60093	Ohm	10 <sup>15</sup>
Melting range		ISO 11357			
DSC	2 <sup>nd</sup> heating			°C	300-315

Pigmentation may affect values.

<sup>1)</sup> C = Complete break, incl. hinge break H

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.