

Product Information

VESTAMID® E47-S1

HEAT- AND LIGHT-STABILIZED COMPOUND BASED ON POLYAMIDE 12 ELASTOMER FOR MOLDING OF SPORT SHOE SOLES



VESTAMID® E47-S1 is a polyamide 12 elastomer consisting of PA 12 segments and softening segments. The material is free of volatile or migrating plasticizer.

The VESTAMID® E represent thermoplastic elastomers generically characterized as polyether block copolyamides (PEBA) consisting of PA 12 and polyether segments.

VESTAMID® E47-S1 is especially developed for sport shoe soles. It has good impact strength at low temperatures.

VESTAMID® E47-S1 is supplied as spherical pellets in moisture-proof packaging, ready for processing.

The process temperatures should be within a range of 180°C – 220°C.

Pigmentation may affect values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Key Features

Industrial Sector

Sustainable, Industry and Engineering, Sports and Lifestyle

Sustainability

Sustainable electricity

Processing

Injection molding, Extrusion

Delivery form

Pellets, Granules

Optics

Translucent

Resistance to

Heat (thermal stability), Hydrolysis / hot water, UV / light / weathering, Wear / abrasion, Fatigue resistance

Additives

Unfilled

LCA-values	dry	Unit	Test Standard
LCA name of certificate	VESTAMID® E mix	-	ISO 14040, 14044
LCA certifier	TÜV Rheinland	-	ISO 14040, 14044
Blue water consumption	14.2	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	6.5	kg CO ₂ eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	6.5	kg CO ₂ eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	0	Annual crop eq. y	ISO 14040, 14044
GWP savings as compared to 2023 reference	-1.6	kg CO ₂ eq./kg	ISO 14040, 14044

Mechanical properties ISO	dry / cond	Unit	Test Standard
Tensile modulus	132 / -	MPa	ISO 527
Tensile strength	27 / -	MPa	ISO 527
Stress at 50% strain	12 / -	MPa	ISO 527
Stress at break	27 / -	MPa	ISO 527
Nominal strain at break, tB	445 / -	%	ISO 527
Charpy impact strength, +23°C	N / -	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	N / -	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	N / -	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	157 / *	°C	ISO 11357-1/-3
Glass transition temperature, DSC	-40 / *	°C	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	45 / *	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	65 / *	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	140 / *	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	70 / *	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	230 / *	E-6/K	ISO 11359-1/-2

Coeff. of linear therm. expansion, 23°C to 55 °C, normal	210 / *	E-6/K	ISO 11359-1/-2
Melting Temperature	157	°C	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	1020 / -	kg/m ³	ISO 1183
Water absorption	1 / *	%	Sim. to ISO 62
Humidity absorption	0.4 / *	%	Sim. to ISO 62
Shore D hardness	46^[b] / -	-	ISO 7619-1
Density	1020	kg/m ³	ASTM D 792

b: 3 seconds

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burnin behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.0 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity, V	1E9 / -	Ohm*m	IEC 62631-3-1
Relative permittivity, 100Hz	8.5 / -	-	IEC 62631-2-1
Relative permittivity, 1MHz	4.7 / -	-	IEC 62631-2-1
Dissipation factor, 100Hz	1200 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	1300 / -	E-4	IEC 62631-2-1
Dielectric strength, AC, S20/P50	37 / -	kV/mm	Sim. to IEC 60243-1

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	28 / *	cm ³ /10min	ISO 1133
Temperature	240 / *	°C	-
Load	2.16 / *	kg	-

Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577
Mold temperature	35 / *	°C	-
Melt temperature	200 / *	°C	-

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	200	°C	ISO 294
Injection Molding, mold temperature	35	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Characteristics

Processing

Film extrusion

Color

Natural color

Special Characteristics

Light-stabilized, High heat resistant

Additives

Plasticizer, Heat stabilizer