

Product Information

## PLEXIGLAS® Resist zk4BR

---

### Product Profile:

PLEXIGLAS® Resist zk4BR is an amorphous, impact-modified thermoplastic molding compound (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are

- excellent weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings

PLEXIGLAS® Resist zk4BR is characterized by the following special properties:

- high break resistance and impact strength
- improved resistance to stress cracking
- balanced property profile
- AMECA listing.

### Application:

Used for extruding and coextruding sheets and profiles as well as for injection molding

### Examples:

extruded and injection-molded luminaire covers, extruded hollow profiles, writing utensils such as stencils and fountain pens, appliance housings, coextruded profiles for window frames, gutters, downspouts, and housewares such as cutlery handles, bowls, cookie jars.

### Processing:

PLEXIGLAS® Resist zk4BR can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

### Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Resist zk4BR
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	2800
Yield Stress	50 mm/min	MPa	ISO 527	71
Yield Strain	50 mm/min	%	ISO 527	4.5
Nominal Strain @ Break		%	ISO 527	19
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	25
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	102
Glass Transition Temperature		°C	ISO 11357	108
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	99
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	95
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	8
Fire Rating			DIN 4102	B2
Flammability UL 94	1.6 mm	Class	IEC 707	HB
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C / 3.8kg	cm <sup>3</sup> /10min	ISO 1133	4.5
<b>Optical Properties</b>				
Luminous transmittance	d=3 mm			
	D65	%	ISO 13468-2	92
Haze			ASTM D1003	< 1.5
Refractive Index			ISO 489	1.49
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.18
Water Absorption in Water		%	ISO 62	2
Humidity Absorption	23°C / 50%	%	ISO 62	0.6
<b>Recommended Processing Conditions</b>				
Predrying Temperature		°C		max. 90
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		220 – 260
Mold Temperature (Injection Molding)		°C		50 – 70

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.