

Product Information

# VESTAKEEP® 4500 G

## HIGH VISCOSITY, UNREINFORCED POLYETHER ETHER KETONE



**VESTAKEEP® 4500 G** is a high viscosity, fast crystallization, unreinforced polyether ether ketone for injection molding and extrusion.

The semi-crystalline polymer features superior, thermal and chemical resistance. Parts made from VESTAKEEP® 4500 G are of low flammability.

VESTAKEEP® 4500 G can be processed by common machines for thermoplastics.

We recommend a melt temperature between 370°C and 380°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 4500 G is supplied as granules in 25kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may affect values.

### Key Features

#### Industrial Sector

Automotive and Mobility, Industry and Engineering, Energy, Oil and Gas

#### Processing

Injection molding, Extrusion

#### Delivery form

Pellets, Granules

#### Optics

Opaque

#### Resistance to

Heat (thermal stability), Fire / burn

#### Electrical

Insulating

#### Conformity

Food contact

#### Additives

Unfilled

Mechanical properties ISO	dry	Unit	Test Standard
Tensile modulus	<b>3800</b>	MPa	ISO 527
Tensile strength	<b>96</b>	MPa	ISO 527
Yield stress	<b>96</b>	MPa	ISO 527
Yield strain	<b>5</b>	%	ISO 527
Strain at break, B	<b>30</b>	%	ISO 527
Nominal strain at break, tB	<b>30</b>	%	ISO 527
Poisson's ratio, 23°C	<b>0.41</b>	-	ISO 527
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-

Thermal properties	dry	Unit	Test Standard
Melting temperature	<b>340</b>	°C	ISO 11357-1/-3
Glass transition temperature, 2 nd heating, midpoint	<b>153</b>	°C	ISO 11357
Temp. of deflection under load A, 1.80 MPa	<b>156</b>	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	<b>232</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	<b>69</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, 23°C to 55 °C, normal	<b>64</b>	E-6/K	ISO 11359-1/-2

Physical properties	dry	Unit	Test Standard
Density	<b>1300</b>	kg/m <sup>3</sup>	ISO 1183
Shore D hardness	<b>86</b>	-	ISO 7619-1

Burning Behav.	dry	Unit	Test Standard
Burnin behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-
Glow Wire Flammability Index (GWFI)	<b>960</b>	°C	IEC 60695-2-12

GWFI - thickness tested	2	mm	-
Glow Wire Ignition Temperature (GWIT)	875	°C	IEC 60695-2-13
GWIT - thickness tested	2	mm	-

Electrical properties	dry	Unit	Test Standard
Volume resistivity, V	>1E13	Ohm*m	IEC 62631-3-1
Relative permittivity, 1MHz	3.3 <sup>[g]</sup>	-	IEC 62631-2-1
Dissipation factor, 1MHz	56 <sup>[g]</sup>	E-4	IEC 62631-2-1
Dielectric strength, AC, S20/S20, t. 1 mm	35.2	kV/mm	IEC 60243-1
Dielectric strength, AC, S20/P25	24.3 <sup>[f]</sup>	kV/mm	IEC 60243-1
Dielectric strength, AC, P25/P25	29.2 <sup>[f]</sup>	kV/mm	IEC 60243-1
Dielectric strength, Short Time	29.4 <sup>[f]</sup>	kV/mm	ASTM D 149
Thickness tested	0.99	mm	-

f: 1 mm thickness  
g: 2 mm thickness

Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	9	cm <sup>3</sup> /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
Mold temperature	180	°C	-
Melt temperature	380	°C	-
Melt viscosity, at 100 1/s	1120	Pa s	-
Temperature	380	°C	-

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	380	°C	ISO 294

Injection Molding, mold temperature

**180**

°C

ISO 294

### Characteristics

#### Applications

General purpose

#### Color

Natural color

#### Processing

Profile extrusion, Sheet extrusion

#### Chemical Resistance

General chemical resistance

#### Special Characteristics

Semi-crystalline, High viscosity

#### Processing Recommendation Injection Molding

	dry	Unit	Test Standard
Pre-drying - Temperature	<b>&lt;150</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>380</b>	°C	-
Mold temperature	<b>180</b>	°C	-
Feed temperature	<b>60</b>	°C	-

#### Processing Recommendation Extrusion

	dry	Unit	Test Standard
--	-----	------	---------------

#### Type of extrusion

Type of extrusion	<b>profile</b>	-	-
-------------------	----------------	---	---

#### Pretreatment

Pre-drying - Temperature	<b>170 - 180</b>	°C	-
Pre-drying - Time	<b>8 - 12</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-

#### Plastification

Feed temperature	<b>60</b>	°C	-
Heating zone 1	<b>350 - 360</b>	°C	-
Heating zone 2	<b>350 - 360</b>	°C	-

Heating zone 3	<b>360 - 370</b>	°C	-
Heating zone 4	<b>360 - 370</b>	°C	-
Heating zone 5	<b>370 - 380</b>	°C	-
Melt temperature	<b>380 - 390</b>	°C	-