

Product Information

VESTAKEEP® i2 P

IMPLANT GRADE VESTAKEEP® POWDER



VESTAKEEP® i2 P is a medium-viscosity polyether ether ketone (PEEK) powder that is designed for long term human implant applications.

Proven Biocompatibility of VESTAKEEP® i-Grades

VESTAKEEP® i2 P is compliant with ASTM F2026 “Standard Specification for Polyetheretherketone (PEEK) Polymers for Surgical Implant Applications”.

The extra high purity and extended quality measures make the i-grades an ideal material for long term body contact.

A summary of biocompatibility tests is available upon request.

Biocompatibility tests available for VESTAKEEP® i2 P

STANDARD	DESCRIPTION
ISO 10993-12	GC/MS Fingerprint of extractable organic substances
USP CLASS VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation
ISO 10993-5	Cytotoxicity
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Maximization test according to Magnusson and Kligman
ISO 10993-11	Subchronic Systemic Toxicity
ISO 10993-3	Genotoxicity: Ames Test
ISO 10993-3	Genotoxicity: Chromosome Aberration test
ISO 10993-3	Genotoxicity: Mouse Lymphoma test
ISO 10993-6	Test for local effects after Implantation in bone (90 days)
ISO 10993-4	Haemocompatibility

In addition to the body contact period the suitability of the material depends on further criteria, for example the nature of the contact, the processing, or the surface. In any case the suitability has to be verified for the end product.

Processing of VESTAKEEP® i-Grades

As a powder, VESTAKEEP® i2 P can be used for compounding, compression molding and other melt processing.

For information about processing of VESTAKEEP® powders, please follow the general recommendations in our brochure “VESTAKEEP® Polyether Ether Ketone Powder”.

Delivery of VESTAKEEP® i-Grades

VESTAKEEP® i2 P is supplied as powder in boxes with moisture-proof polyethylene liners.

Rheological properties

	dry	Unit	Test Standard
Melt volume-flow rate, MVR	70	cm ³ /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-

Test specimen production

	dry	Unit	Test Standard
Injection Molding, melt temperature	380	°C	ISO 294
Injection Molding, mold temperature	180	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Characteristics

Regulatory

US Pharmacopeia Class VI conformity

Chemical Resistance

General chemical resistance

Color

Natural color