

Product Information

VESTODUR® X4159

POLYBUTYLENE TEREPHTHALATE RESIN WITH HIGH FLEXIBILITY AND IMPACT RESISTANCE



VESTODUR® X4159 is a high viscosity semi-crystalline thermoplastic polyester resin based on modified polybutylene terephthalate (PBT). Test bars made of this resin have high flexibility and impact resistance.

VESTODUR® X4159 is supplied as cylindrical pellets in polyethylene packaging.

The use of colorants may affect property values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Key Features

Industrial Sector
Automotive and Mobility

Conformity
Automotive

Processing
Injection molding, Extrusion

Additives
Unfilled

Delivery form
Pellets, Granules

Mechanical properties ISO

| | dry / cond | Unit | Test Standard |
|-----------------------------|-------------------|-------------|----------------------|
| Tensile modulus | 500 / 580 | MPa | ISO 527 |
| Yield stress | 27 / - | MPa | ISO 527 |
| Yield strain | 25 / - | % | ISO 527 |
| Stress at break | * / 19 | MPa | ISO 527 |
| Nominal strain at break, tB | >50 / 4 | % | ISO 527 |

| | | | |
|--|------------------|-------------------|-------------|
| Charpy impact strength, +23°C | N / 45 | kJ/m ² | ISO 179/1eU |
| Type of failure | - / C | - | - |
| Charpy impact strength, -30°C | N / 21 | kJ/m ² | ISO 179/1eU |
| Type of failure | - / C | - | - |
| Charpy notched impact strength, +23°C | 30 / 3 | kJ/m ² | ISO 179/1eA |
| Type of failure | C / C | - | - |
| Charpy notched impact strength, -30°C | 8 / 1 | kJ/m ² | ISO 179/1eA |
| Type of failure | C / C | - | - |
| Flexural modulus, 23°C | 490 / 590 | MPa | ISO 178 |
| Flexural stress at conv. deflection, 23°C | 16 / 20 | MPa | ISO 178 |
| Flexural strength, 23°C | 25 / 28 | MPa | ISO 178 |
| Flexural strain at flexural strength, 23°C | 9 / 6 | % | ISO 178 |
| Flexural stress at break, 23°C | N / 28 | MPa | ISO 178 |
| Flexural strain at break, 23°C | N / 6 | % | ISO 178 |

| Thermal properties | dry / cond | Unit | Test Standard |
|--|-------------------|-------------|----------------------|
| Melting temperature | 200 / * | °C | ISO 11357-1/-3 |
| Temp. of deflection under load A, 1.80 MPa | 50 / * | °C | ISO 75-1/-2 |
| Temp. of deflection under load B, 0.45 MPa | 110 / * | °C | ISO 75-1/-2 |
| Vicat softening temperature A, 10 N, 50 K/h | 190 / * | °C | ISO 306 |
| Vicat softening temperature B, 50 N, 50 K/h | 130 / * | °C | ISO 306 |
| Coeff. of linear therm. expansion, 23°C to 55 °C, parallel | 120 / * | E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, 23°C to 55 °C, normal | 120 / * | E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, -40°C to +100°C, parallel | 120 | E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, -40°C to +100°C, normal | 120 | E-6/K | ISO 11359-1/-2 |
| Melting Temperature | 200 | °C | ASTM D 3418 |

| Physical properties | dry / cond | Unit | Test Standard |
|---------------------|-----------------------|-------------------|----------------|
| Density | 1260 / - | kg/m ³ | ISO 1183 |
| Water absorption | 0.4 / * | % | Sim. to ISO 62 |
| Humidity absorption | 0.3 / * | % | Sim. to ISO 62 |
| Shore D hardness | 70 ^[b] / - | - | ISO 7619-1 |
| Density | 1260 | kg/m ³ | ASTM D 792 |

b: 3 seconds

| Burning Behav. | dry / cond | Unit | Test Standard |
|---------------------------------------|------------|-------|-----------------|
| Burning behav. at 1.5 mm nom. thickn. | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 1.6 / * | mm | - |
| Burning behav. at thickness h | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 0.8 / * | mm | - |
| Oxygen index | 25 / * | % | ISO 4589-1/-2 |
| Limiting Oxygen Index | 25 | % | ASTM D 2863 |

| Electrical properties | dry / cond | Unit | Test Standard |
|--------------------------------------|------------|-------|----------------|
| Volume resistivity, V | 1E11 / - | Ohm*m | IEC 62631-3-1 |
| Surface resistance, RSD | 1E14 / - | Ohm | IEC 62631-3-2 |
| Relative permittivity, 100Hz | 4 / - | - | IEC 62631-2-1 |
| Dissipation factor, 100Hz | 350 / - | E-4 | IEC 62631-2-1 |
| CTI, test solution A, 50 drops value | 600 / - | - | IEC 60112 |
| Assessment of the insulation group | I | - | DIN EN 60664-1 |

| Rheological properties | dry / cond | Unit | Test Standard |
|-----------------------------|------------|------------------------|-----------------|
| Melt volume-flow rate, MVR | 10 / * | cm ³ /10min | ISO 1133 |
| Temperature | 250 / * | °C | - |
| Load | 2.16 / * | kg | - |
| Molding shrinkage, parallel | 2.0 / * | % | ISO 294-4, 2577 |

Molding shrinkage, normal

2.0 / *

%

ISO 294-4, 2577

Characteristics

Applications

Tube and hose

Special Characteristics

High impact strength, High viscosity

Processing

Film extrusion, Profile extrusion

Color

Natural color

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)
- ✗ Hydrochloric Acid (36% by mass) (23°C)
- ✗ Nitric Acid (40% by mass) (23°C)
- ✓ Sulfuric Acid (38% by mass) (23°C)
- ✓ Sulfuric Acid (5% by mass) (23°C)

Bases

- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✗ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

Hydrocarbons

- ✓ iso-Octane (23°C)

Ketones

- ✗ Acetone (23°C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ Insulating Oil (23°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)

Other

- ✓ Water (23°C)
- ✗ Deionized water (90°C)

Rheological calculation properties

| | dry | Unit | Test Standard |
|-----------------------|------------|-------------|----------------------|
| Min. mold temperature | 50 | °C | - |
| Max. mold temperature | 120 | °C | - |
| Min. melt temperature | 240 | °C | - |
| Max. melt temperature | 270 | °C | - |