

Product Information

# VESTAMID® DX9304 BK E70238

## HIGH-VISCOSITY, HEAT- AND LIGHT-STABILIZED, IMPACT-MODIFIED POLYAMIDE 612 COMPOUND FOR EXTRUSION

**VESTAMID® DX9304 BK E70238** is a PA 612 extrusion compound developed for the manufacturing of tubing systems with higher demands on heat resistance.

The melting point of VESTAMID® DX9304 BK E70238, about 35 °C higher than PA 11 and PA 12 compounds, allows higher temperatures in use. The compound is especially suitable for the extrusion of tubing systems that are exposed to high burst pressures at high service temperatures, e.g. hydraulic clutch lines.

The material absorbs only little moisture. Therefore dimensions and properties of parts are nearly unaffected through ambient conditions.

The process temperatures should be in the range of 240-270°C.

Pigmentation may affect values.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

### Key Features

#### Industrial Sector

Automotive and Mobility, Sustainable, Industry and Engineering

#### Sustainability

Sustainable electricity

#### Processing

Extrusion

#### Delivery form

Pellets, Granules

#### Resistance to

Heat (thermal stability), UV / light / weathering, Oil / fuels

#### Electrical

Insulating

#### Conformity

Automotive

#### Additives

Unfilled

LCA-values	dry	Unit	Test Standard
LCA name of certificate	<a href="#">VESTAMID® D Compound medium</a>	-	ISO 14040, 14044
LCA certifier	<a href="#">TÜV Rheinland</a>	-	ISO 14040, 14044
Blue water consumption	<b>21.7</b>	kg	ISO 14040, 14044
Global Warming Potential incl. bio. C incl. LUC	<b>7.2</b>	kg CO <sub>2</sub> eq./kg	ISO 14040, 14044
Global Warming Potential excl. bio. C incl. LUC	<b>7.2</b>	kg CO <sub>2</sub> eq./kg	ISO 14040, 14044
Land use (ReCiPe 2016)	<b>0.1</b>	Annual crop eq. y	ISO 14040, 14044
GWP savings as compared to 2023 reference	<b>-2.1</b>	kg CO <sub>2</sub> eq./kg	ISO 14040, 14044

Mechanical properties ISO	dry / cond	Unit	Test Standard
Tensile modulus	<b>1850 / 1200</b>	MPa	ISO 527
Tensile strength	<b>50 / -</b>	MPa	ISO 527
Yield stress	<b>50 / 41</b>	MPa	ISO 527
Yield strain	<b>5 / 20</b>	%	ISO 527
Stress at break	<b>43 / *</b>	MPa	ISO 527
Nominal strain at break, tB	<b>41 / &gt;50</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>40 / 95</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>P / P</b>	-	-
Charpy notched impact strength, -30°C	<b>30 / 18</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C / C</b>	-	-
Flexural modulus, 23°C	<b>1820 / 1050</b>	MPa	ISO 178
Flexural stress at conv. deflection, 23°C	<b>58 / 32</b>	MPa	ISO 178
Flexural strength, 23°C	<b>72 / 44</b>	MPa	ISO 178
Flexural strain at flexural strength, 23°C	<b>7 / 8</b>	%	ISO 178
Flexural stress at break, 23°C	<b>N / N</b>	MPa	ISO 178

Flexural strain at break, 23°C	N / N	%	ISO 178
--------------------------------	-------	---	---------

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	213 / *	°C	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	50 / *	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	170 / *	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	209 / *	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	175 / *	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	150 / *	E-6/K	ISO 11359-1/-2
Melting Temperature	213	°C	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	1040 / 1040	kg/m <sup>3</sup>	ISO 1183
Water absorption	2.7 / *	%	Sim. to ISO 62
Humidity absorption	1.3 / *	%	Sim. to ISO 62
Shore D hardness	75 <sup>[b]</sup> / 74 <sup>[b]</sup>	-	ISO 7619-1
Density	1040	kg/m <sup>3</sup>	ASTM D 792

b: 3 seconds

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burnin behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.2 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity, V	3.2E12 / 1.8E10	Ohm*m	IEC 62631-3-1
Surface resistivity, C, circular electrodes	1.3E14 / 1.4E14	Ohm per square	IEC 62631-3-2
Relative permittivity, 50Hz	4.2 / -	-	IEC 62631-2-1

Relative permittivity, 100Hz	4.1 / -	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.2 / -	-	IEC 62631-2-1
Dissipation factor, 50Hz	690 / -	E-4	IEC 62631-2-1
Dissipation factor, 100Hz	560 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	310 / -	E-4	IEC 62631-2-1
Dielectric strength, AC, S20/S20, t. 1 mm	39 / 38	kV/mm	IEC 60243-1
CTI, test solution A, 50 drops value	600 / -	-	IEC 60112
Assessment of the insulation group	I	-	DIN EN 60664-1

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	7 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	280 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	2.1 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577
Mold temperature	80 / *	°C	-
Melt temperature	260 / *	°C	-

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

### Characteristics

#### Applications

Tube and hose

#### Color

Black

#### Processing

Profile extrusion

#### Additives

Impact resistant, Light stabilizer, Heat stabilizer

### Special Characteristics

High impact strength, Light-stabilized, High heat resistant,  
High viscosity

### Chemical Media Resistance

#### Acids

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)

#### Bases

- ✓ Sodium Hydroxide solution (35% by mass) (23°C)
- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23°C)

#### Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

#### Hydrocarbons

- ✓ n-Hexane (23°C)
- ✓ Toluene (23°C)
- ✓ iso-Octane (23°C)

#### Ketones

- ✓ Acetone (23°C)

#### Ethers

- ✓ Diethyl ether (23°C)

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ Insulating Oil (23°C)

#### Standard Fuels

- ✓ ISO 1817 Liquid 1 (60°C)
- ✓ ISO 1817 Liquid 2 (60°C)
- ✓ ISO 1817 Liquid 3 (60°C)

- ✓ ISO 1817 Liquid 4 (60°C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✓ Diesel EN 590 (100°C)

#### Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

#### Other

- ✓ Ethyl Acetate (23°C)
- ✓ Hydrogen peroxide (23°C)
- ✓ DOT No. 4 Brake fluid (120°C)
- ✓ Water (23°C)