

Product Information

VESTAMID® NRG 2902 BK

FOR GAS PIPE FITTINGS



VESTAMID® NRG 2902 BK is a high viscosity, heat stabilized and UV stabilized compound, based on PA12, with exceptional mold release properties. Additionally, VESTAMID® NRG 2902 BK is nucleated to reduce the cycle time and shrinkage of molded parts. Parts made of this semi-crystalline material are characterized by good impact strength, high abrasion resistance, low friction and good chemical resistance. In general, mechanical properties of compounds based on PA 12 vary little with changing humidity due to their low moisture absorption.

VESTAMID® NRG 2902 BK is suitable for molding gas pipe fittings. Polyamide 12 is a high performance thermoplastic polymer with increased performance characteristics that translates into safe operations over the life of the installed pipeline. It has a considerable record of safe and proven experience in many demanding applications, including fuel lines in passenger cars, air brake tubing in trucks and off-shore applications.

A processing temperature between 230 °C and 260 °C - in some cases up to 280 °C - is recommended during the injection molding process. The mold temperature should be within a range of 60 °C to 100 °C. It is recommended to dry the material before processing for 2 to 4 hours at 80 °C.

VESTAMID® NRG 2902 BK is delivered as granules in ready-to-process condition in moisture-tight packaging. Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

The results presented were generated from a small number of production lots. They are therefore provisional and not yet the result of a statistical analysis.

The values presented are typical or average values, they do not constitute a specification.

Key Features

Industrial Sector

Energy, Oil and Gas

Processing

Injection molding

Delivery form

Pellets, Granules

Optics

Opaque

Resistance to

Heat (thermal stability), UV / light / weathering

Additives

Lubricant, Release agent

VESTAMID® NRG

Mechanical properties ISO	dry	Unit	Test Standard
Tensile modulus	1300	MPa	ISO 527
Tensile strength	48	MPa	ISO 527
Yield stress	38	MPa	ISO 527
Yield strain	12	%	ISO 527
Stress at 50% strain	32	MPa	ISO 527
Nominal strain at break, tB	245	%	ISO 527
Charpy notched impact strength, +23°C	44	kJ/m ²	ISO 179/1eA
Type of failure	P	-	-

Thermal properties	dry	Unit	Test Standard
Melting temperature	177	°C	ISO 11357-1/-3

Physical properties	dry	Unit	Test Standard
Density	1010	kg/m ³	ISO 1183
Moisture content	0.04	Gew.-%	ISO 15512
Bulk density, Granulate	579	kg/m ³	-
Weight per 1000 granules	15	g	-

Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	38	cm ³ /10min	ISO 1133
Temperature	240	°C	-
Load	10	kg	-

Polymer analytics	dry	Unit	Test Standard
Viscosity number	169	cm ³ /g	ISO 307, 1157, 1628

Characteristics

Applications
Fittings

Additives
Release agent