

Luran 388S

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

DESCRIPTION

Luran® 388S is a specialty grade of SAN with enhanced chemical resistance and the highest mechanical strength. It is suitable for injection molding and extrusion applications.

FEATURES

- Very good chemical resistance
- Very good mechanical strength
- Good surface appearance
- Good heat resistance
- Excellent transparency
- Excellent dimensional stability

APPLICATIONS

- Battery housings
- Storage boxes
- Toilet seats
- Sanitary equipment
- Kitchen robot

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	7
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	2.5
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	2.5
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	2.5
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	21
Charpy Unnotched, -30 °C	ISO 179/1eU	kJ/m ²	19
Tensile Stress at Yield, 23 °C	ISO 527	MPa	79
Tensile Strain at Break, 23 °C	ISO 527	%	4
Tensile Modulus	ISO 527	MPa	3800
Tensile Creep Modulus (1000h)	ISO 899	MPa	2800
Tensile Creep Modulus (1h)	ISO 899	MPa	3500
Flexural Strength, 23 °C	ISO 178	MPa	140
Hardness, Ball Indentation	ISO 2039-1	MPa	175
Thermal Properties			

Luran 388S

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	107
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	90
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	102
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	70
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 62631-2-1	-	3
Dissipation Factor (100 Hz)	IEC 62631-2-1	10 ⁻⁴	50
Dissipation Factor (1 MHz)	IEC 62631-2-1	10 ⁻⁴	80
Volume Resistivity	IEC 62631-3-1	Ohm*m	10 ¹⁴
Surface Resistivity	IEC 62631-3-1	Ohm	>10 ¹⁵
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.56
Other Properties			
Density	ISO 1183	kg/m ³	1080
Bulk Density (with external lubricant)	-	kg/m ³	650
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.3
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 0.7
Melt Temperature Range	ISO 294	°C	220 - 260
Mold Temperature Range	ISO 294	°C	40 - 80
Injection Velocity	ISO 294	mm/s	200
Drying Temperature	-	°C	80
Drying Time	-	h	2 - 4