

Luran 388S

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

DESCRIPTION

Luran® 388S is a specialty grade of SAN with enhanced chemical resistance and the highest mechanical strength. It is suitable for injection molding and extrusion applications. Food contact statements are available on request.

FEATURES

- Chemical resistance
- Heat resistance
- Transparency

APPLICATIONS

- Food contact applications
- Industrial batteries
- Sanitary housings

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	7
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	2.5
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	21
Charpy Unnotched, -30 °C	ISO 179/1eU	kJ/m ²	19
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	2.5
Tensile Modulus	ISO 527	MPa	3800
Tensile Stress at Yield, 23 °C	ISO 527	MPa	79
Flexural Modulus, 23 °C	ISO 178	MPa	3700
Flexural Strength, 23 °C	ISO 178	MPa	140
Hardness, Ball Indentation	ISO 2039-1	MPa	175
Tensile Strain at Break, 23 °C	ISO 527	%	4
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	107
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	101
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	102
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	70

Luran 388S

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Thermal Conductivity	ISO 22007-4	W/(m K)	0.17
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.56
Haze	ASTM D 1003	%	< 1
Light Transmission at 550 nm	ASTM D 1003	%	> 89
Other Properties			
Density	ISO 1183	kg/m ³	1080
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.3
Processing			
Melt Temperature Range	ISO 294	°C	220 - 260
Mold Temperature Range	ISO 294	°C	40 - 80
Drying Temperature	-	°C	80
Drying Time	-	h	2 - 4
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 0.7