

Absolac 30GF30%

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

DESCRIPTION

Absolac® 30GF 30 is a glass filled grade

FEATURES

- Glass filled

APPLICATIONS

- Pulleys
- Telex terminals
- Video & Audio Cassette knobs
- AC Fan blades
- Blowers

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 220 °C/10 kg	ISO 1133	g/10 min	8
Mechanical Properties			
Izod Notched Impact Strength, 1/4" bar, 0.010" Notch Radius, 23 °C (73 °F)			6
Tensile Stress at Yield, 23 °C	ISO 527	MPa	min 70
Tensile Modulus (MD)	ISO 527	MPa	7200
Flexural Strength, 23 °C	ISO 178	MPa	93
Flexural Modulus, 23 °C	ISO 178	MPa	5100
Hardness, Rockwell	ISO 2039-2	R scale	115
Thermal Properties			
Vicat Softening Temperature, VST/A/50 (10N, 50°C/h)	ISO 306	°C	113
Vicat Softening Temperature, B/2 (120 °C/h, 50N)	ASTM D 1525	°C	105
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	103
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	105
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	50 to 60
Optical Properties			
Specular Gloss, 60 °	ASTM D 523	%	+98

Absolac 30GF30%

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Other Properties			
Density	ISO 1183	kg/m ³	1210
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.1 to 0.3