

Terluran ECO GP-22 BC60

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

DESCRIPTION

Terluran® ECO GP-22 BC60 is an easy-flow, general purpose injection molding grade with high resistance to impact and heat distortion; intended for a wide range of applications, particularly in the housings sector. Terluran ECO GP-22 BC60 is an ISCC compliant product leading to a substitution of fossil source styrene with attributed ISCC certified bio-circular styrene.

FEATURES

- Excellent colorability
- Medium flow
- Good impact resistance
- Good heat distortion resistance
- High quality surface finish and gloss
- Great mechanical strength and rigidity

APPLICATIONS

- Injection molding
- Appliance housings
- Household and sanitary appliances
- Toys
- Automotive components
- Consumer products

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	19
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	26
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	8
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	22
Charpy Notched Impact Strength, -30 °C	ISO 179/1eA	kJ/m ²	8
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	180
Charpy Unnotched, -30 °C	ISO 179/1eU	kJ/m ²	100
Tensile Stress at Yield, 23 °C	ISO 527	MPa	45
Tensile Strain at Yield, 23 °C	ISO 527	%	2.6
Tensile Modulus	ISO 527	MPa	2300
Nominal Strain at Break, 23 °C	ISO 527	%	10
Flexural Strength, 23 °C	ISO 178	MPa	65

Terluran ECO GP-22 BC60

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Hardness, Ball Indentation	ISO 2039-1	MPa	97
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	96
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	105
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	94
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	99
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	80 - 110
Thermal Conductivity	ISO 22007-4	W/(m K)	0.17
Electrical Properties			
Dissipation Factor (100 Hz)	IEC 62631-2-1	10 ⁻⁴	48
Dissipation Factor (1 MHz)	IEC 62631-2-1	10 ⁻⁴	79
Relative Permittivity (100 Hz)	IEC 62631-2-1	-	2.9
Relative Permittivity (1 MHz)	IEC 62631-2-1	-	2.8
Volume Resistivity	IEC 62631-3-1	Ohm*m	>10 ¹³
Surface Resistivity	IEC 62631-3-1	Ohm	>10 ¹³
Optical Properties			
Yellowness Index	DIN 6167	-	13
Other Properties			
Density	ISO 1183	kg/m ³	1040
Water Absorption, Saturated at 23 °C	ISO 62	%	1
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.22
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	220 - 260
Mold Temperature Range	ISO 294	°C	30 - 80
Injection Velocity	ISO 294	mm/s	200
Drying Temperature	-	°C	80

Terluran ECO GP-22 BC60

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Drying Time	-	h	2 - 4