



240-GA09

Product Technical Information

Polypropylene **240-GA09** is a random copolymer polypropylene with a Melt Flow Index of 9 g/10 min for the cast extrusion of films with excellent heat weldability and optical properties.

Polypropylene **240-GA09** is intended for food, magazine or textile packaging, for lamination films... as well as for stationary supplies.

Characteristics

Properties	Test Methods	Values	Units
Rheological			
Melt Flow Rate 230°C/2.16Kg	ISO 1133	9	g/10 min
Mechanical			
Flexural modulus	ISO 178	850	MPa
Thermal			
Melting Point	ISO 3146	140	°C
Other physical properties			
Density	ISO 1183	0.902	g/cm ³
Bulk Density	ISO 60	0.525	g/cm ³
Data should not be used for specification work			

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.