



# 200-CA25

## Product Technical Information

Polypropylene Random Copolymer

### Benefits & Features

**200-CA25** is a clarified random copolymer with a medium ethylene content and good flow primarily intended for injection moulding of clear articles. 200-CA25 has a property profile also suitable for injection stretch blow moulding (ISBM).

- Clarified
- Antistatic
- Good flow

### Applications

- Transparent thin wall injection moulding
- Caps and closures
- Housewares
- Clarified food containers
- ISBM Bottles

Properties	Conditions	Test Methods	Values	Units
<b>Physical</b>				
Melt Flow Rate	230°C/2.16Kg	ISO 1133-1	25	g/10min
<b>Mechanical*</b>				
Flexural Modulus	23°C	ISO 178	1100	MPa
Tensile Strength at Yield	23°C	ISO 527-1,-2	28	MPa
Izod Impact Strength, notched	23°C	ISO 180/A	5.5	KJ/m <sup>2</sup>
Izod Impact Strength, notched	0°C	ISO 180/A	2.8	KJ/m <sup>2</sup>
<b>Optical</b>				
Haze	1mm Thickness	ASTM D 1003	15	%
Haze	2mm Thickness	ASTM D 1003	30	%
<b>Thermal</b>				
Crystallisation Temperature	DSC	INEOS Test Method	119	°C
Heat Deflection Temperature	0.45 MPa	ISO 75-2	85	°C
Vicat Softening Temperature	10N	ISO306/A50	129	°C

**Data should not be used for specification work**

\* Values determined on injection moulded specimens acc. to ISO 1873-2, based on 7 days conditioning time

### Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.