



200-SB08

Product Technical Information

Polypropylene 200-SB08 is a random copolymer polypropylene with a Melt Flow Index of 8 g/10 min for the cast extrusion of films with very good optical properties and easy heat weldability.

Polypropylene 200-SB08 is formulated with slip and anti-block agents. It is intended for food, magazine or textile packaging, for lamination films... as well as for stationary supplies.

Characteristics

Properties	Test Methods	Values	Units
Rheological			
Melt Flow Rate 230°C/2.16Kg	ISO 1133	8	g/10 min
Mechanical			
Tensile Strength at Yield	ISO 527-2	27	MPa
Elongation at Yield	ISO 527-2	10	%
Tensile modulus	ISO 527-2	1050	MPa
Flexural modulus	ISO 178	950	MPa
Izod Impact Strength (notched) at 23°C	ISO 180	6	kJ/m ²
Charpy Impact Strength (notched) at 23°C	ISO 179	8	kJ/m ²
Hardness Rockwell - R-scale	ISO 2039-2	86	
Thermal			
Melting Point	ISO 3146	145	°C
Vicat Softening Point 10N-50°C per hour	ISO 306	136	°C
Other physical properties			
Density	ISO 1183	0.905	g/cm ³
Bulk Density	ISO 60	0.525	g/cm ³

Data should not be used for specification work



200-SB08

Additional Properties: typical film properties on 50µm thick cast film

Properties	Test Methods	Values	Units
Optical			
Gloss 45°	ASTM D2457	89	
Haze	ISO 14782	1.2	%
Mechanical*			
Tensile Strength at Yield MD / TD *	ISO 527-3	18 / 18	MPa
Tensile Strength at Break MD / TD *	ISO 527-3	36 / 26	MPa
Tensile Elongation at Break MD / TD *	ISO 527-3	500 / 470	%
Dart Impact	ISO 7765-1	320	g
Elmendorf MD / TD	ISO 6383-2	15 / 30	N/mm
Data should not be used for specification work			

* MD: Machine Direction

TD: Transverse Direction

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.