



# 101-ZB25

## Product Technical Information

Polypropylene - Homopolymer.

### Benefits & Features

**101-ZB25** is a polypropylene homopolymer grade fibre grade with a nominal MFR of 25. It has a medium to narrow MWD which makes it suitable for high speed spinning processes.

- Non yellowing / anti-gasfading
- Good processability
- High degree of cleanliness
- Low catalyst residues

### Applications

- Industrial Spunbond Nonwovens.

Properties	Conditions	Test Methods	Values	Units
<b>Rheological</b>				
Melt Flow Rate	230°C/2.16Kg	ISO 1133-1	25	g/10min
<b>Thermal</b>				
Melting Temperature	DSC 2nd heating 10°C/min	ISO 11357-3	160	°C
<b>Data should not be used for specification work</b>				

### Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.