

ELTEX[®] P KS607

Product Technical Information

Polypropylene - Heat Seal

Benefits & Features

- **ELTEX[®] P KS607** is a resin with enhanced surface properties, specifically developed for the metal receptive skin layer in metallised film applications. This resin is also specifically designed to achieve good treatment retention over time before and after metallisation as well as good barrier properties on metallised film. Its well adapted composition allows film with improved haze and gloss properties to be produced.

Applications

- Butene copolymer for metallisable skin layer in coextruded film

Properties	Conditions	Test Methods	Values	Units
Physical				
Melt Flow Rate	230°C/2.16Kg	ISO 1133-1	5	g/10min
Density	23°C	ISO 1183-1	895	kg/m ³
Mechanical				
Flexural Modulus	23°C	ISO 178	850	MPa
Tensile Strength at Yield	23°C	ISO 527-1,-2	27	MPa
Shore D Hardness	23°C	ISO 868	65	-
Thermal				
Melting Point		ASTM D 3417	145	°C
Vicat Softening Temperature	10 N	ISO306/A50	129	°C
Heat Deflection Temperature	0.45 MPa	ISO 75-2	70	°C
Heat Seal Threshold	1s, 3 bars, 100mm/min & 100g/cm	Ineos Method	121	°C
Data should not be used for specification work				

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.