



Eltex[®] P KS409

Product Technical Information

Polypropylene - Heat Seal

Benefits & Features

Eltex[®] P KS409 is a random copolymer with a high ethylene content, developed for use primarily as the sealing layer in "coextruded bioriented film". It contains no special additives and is thus particularly appreciated by users wishing to use their own "formulas".

Applications

- Random copolymer specially developed for the sealing layers of "coextruded bioriented film", suitable also for coextruded cast film

Properties	Conditions	Test Methods	Values	Units
Physical				
Melt Flow Rate	230°C/2.16Kg	ISO 1133-1	5	g/10min
Density	23°C	ISO 1183-1	895	kg/m ³
Mechanical				
Flexural Modulus	23°C	ISO 178	700	MPa
Tensile Strength at Yield	23°C	ISO 527-1,-2	21	MPa
Shore D Hardness	23°C	ISO 868	62	-
Thermal				
Melting Point		ASTM D 3417	134	°C
Vicat Softening Temperature	10 N	ISO306/A50	120	°C
Heat Deflection Temperature	0.45 MPa	ISO 75-2	60	°C
Heat Seal Threshold	1s, 3 bars, 100mm/min & 100g/cm	Ineos Method	115	°C

Data should not be used for specification work

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.