



# ELTEX<sup>®</sup> PF0102XA

## Provisional Product Technical Information

ELTEX<sup>®</sup> PF0102XA is a metallocene polyethylene plastomer resin produced in Europe

## Benefits & Features

ELTEX<sup>®</sup> PF0102XA is a polyethylene copolymer containing hexene-1 as comonomer and produced with a metallocene catalyst. It offers the following properties:

- Extremely low sealing initiation temperature and excellent Hot Tack strength
- Unrivalled impact strength and puncture resistance
- Very high gloss and transparency
- Softness and flexibility
- Excellent blending compatibility with other polyolefin grades

## Applications

ELTEX<sup>®</sup> PF0102XA has been developed for use in highly technical blown and cast film like food packaging, lamination and co-extrusion applications where superior mechanical and sealing performance is required.

ELTEX<sup>®</sup> PF0102XA can be used pure or as a blending partner with other polyolefins. In addition, ELTEX<sup>®</sup> PF0102XA offers easy extrudability.

ELTEX<sup>®</sup> PF0102XA is also recommended as a softening agent in film and non-film compositions requiring softness or flexibility like compounds for wire and cable applications. The very low density and the unique microstructure of ELTEX<sup>®</sup> PF0102XA are also valuable as toughness enhancer in various applications, including polypropylene moulding.

We recommend that you consult your INEOS technical representative for further advice on the use of ELTEX<sup>®</sup> PF0102XA.

Properties	Conditions	Test Methods	Values	Units
<b>Rheological</b>				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	1.9	g/10min
<b>Physical</b>				
Density ISO 1872-1	23°C	ISO 1183-2	902	kg/m <sup>3</sup>
<b>Thermal</b>				
Peaks melting temperature (DSC)		INEOS Test Method	85 – 111	°C
Vicat Softening temperature	10N	ISO306/A50	79	°C
<b>Additives</b>				
Antioxidants				
<b>Data should not be used for specification work</b>				



# ELTEX<sup>®</sup> PF0102XA

## Processing guidelines

**ELTEX<sup>®</sup> PF0102XA** should be processed on machinery purpose designed for LLDPE. Melt temperatures in the range 190 - 250°C can be used.

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.