



ELTEX[®] PF1315AZ

Product Technical Information

Additive free C6 m-LLDPE for extrusion coating, injection moulding and compounding.

Benefits & Features

- outstanding ESCR performance
- improved sealing performance
- improved mechanical properties

Applications

For extrusion coating:

- extrusion coating polymer for high demand on sealing and mechanical performance

For injection moulding and compounding:

- absence of any kind of additive allowing tailor formulation of specific compounds and master-batches

We recommend that you consult your INEOS technical representative for further advice on the use of **ELTEX[®] PF1315AZ**.

Properties	Conditions	Test Methods	Values	Units
Rheological				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	15	g/10min
Physical				
Density ISO 1872-1	23°C	ISO 1183-1	914	kg/m ³
Mechanical*				
Shore hardness D		ISO 868	46	-
Tensile Modulus		ISO 527-2	217	MPa
Tensile Strength at Yield	23°C	ISO 527-1,-2	9	MPa
Tensile strain at Yield		ISO 527-2	22	%
Tensile strength at Break		ISO 527-2	No break	MPa
Tensile strain at Break		ISO 527-2	>600	%
Flexural Modulus	23°C	ISO 178	244	MPa
Izod Impact Strength, notched	-20°C	ISO 180/A	71	kJ/m ²
Environmental Stress Crack Resistance		INEOS Test Method	175	h
Thermal				
Melting Temperature	DSC 2nd heating 10°C/min	ISO 11357-3	96 - 114	°C
Heat of Fusion		ASTM 3418	104	J/g
Crystallization Temperature		INEOS Test Method	100 - 84	°C
Vicat Softening Temperature	10N	ISO306/A50	90	°C

Data should not be used for specification work

* Measurements made on compression moulded plaques



ELTEX[®] PF1315AZ

Processing guidelines

For extrusion coating it is recommended to avoid extrusion temperatures above 280°C, not to jeopardize the sealing properties.

For injection moulding it is recommended to avoid extrusion temperatures above 280°C.

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration.

It is advised to process the product within maximum one year after delivery.