



## Product Technical Information

C6 m-LLDPE for extrusion coating, injection moulding and compounding with a basic antioxidant additive package.

### Benefits & Features

- outstanding ESCR performance
- improved sealing performance
- improved mechanical properties

### Applications

- extrusion coating polymer for high demand on sealing and mechanical performance

We recommend that you consult your INEOS technical representative for further advice on the use of **ELTEX® PF1315AA**.

Properties	Conditions	Test Methods	Values	Units
<b>Rheological</b>				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	15	g/10min
<b>Physical</b>				
Density ISO 1872-1	23°C	ISO 1183-1	914	kg/m <sup>3</sup>
<b>Mechanical*</b>				
Shore hardness D		ISO 868	46	-
Tensile Modulus		ISO 527-2	217	MPa
Tensile Strength at Yield	23°C	ISO 527-1,-2	9	MPa
Tensile strain at Yield		ISO 527-2	22	%
Tensile strength at Break		ISO 527-2	No break	MPa
Tensile strain at Break		ISO 527-2	>600	%
Flexural Modulus	23°C	ISO 178	244	MPa
Izod Impact Strength, notched	-20°C	ISO 180/A	71	kJ/m <sup>2</sup>
Environmental Stress Crack Resistance		INEOS Test Method	175	h
<b>Thermal</b>				
Melting Temperature	DSC 2nd heating 10°C/min	ISO 11357-3	96 - 114	°C
Heat of Fusion		ASTM 3418	104	J/g
Crystallization Temperature		INEOS Test Method	100 - 84	°C
Vicat Softening Temperature	10N	ISO306/A50	90	°C

**Data should not be used for specification work**

\* Measurements made on compression moulded plaques



# ELTEX<sup>®</sup> PF1315AA

## Processing guidelines

For extrusion coating it is recommended to avoid extrusion temperatures above 280°C, not to jeopardize the sealing properties.

For injection moulding it is recommended to avoid extrusion temperatures above 280°C.

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration.

It is advised to process the product within maximum one year after delivery.