



18R430

Product Technical Information

Additive free LDPE homopolymer extrusion coating, injection moulding and compounding product

Benefits & Features

18R430 special polymer structure gives the following properties:

For extrusion coating:

- Well balanced Neck In and Draw Down performance
- Good adhesion performance and sealing properties
- Excellent substrate wettability

For injection moulding and compounding:

- Excellent flexibility
- Good transparency
- Absence of any kind of additive allowing tailor formulation of specific compounds and master-batches

Applications

Extrusion coating and laminating grade designed for a medium to high coating line speed.

18R430 is also suitable for injection moulding of flexible products (caps and closures, food containers, soft tubes, technical parts) as well as for the production of compounds.

We recommend that you consult your INEOS technical representative for further advice on the use of **18R430**.

Properties	Conditions	Test Methods	Values	Units
Rheological				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	15	g/10min
Physical				
Density ISO 1872-1	23°C	ISO 1183-1	919	kg/m ³
Mechanical *				
Shore Hardness D	1 second	ISO 868	40	-
Tensile strength at yield	23°C, 50mm/min	ISO 527-2	8	MPa
Tensile strength at break	23°C, 50mm/min	ISO 527-2	10	MPa
Tensile strain at Break	23°C, 50mm/min	ISO 527-2	400	%
Thermal				
Melting Temperature	DSC 2nd heating 10°C/min	ISO 11357-3	107	°C
Vicat Softening Temperature	10N	ISO306/A50	78	°C
Data should not be used for specification work				

* Measurements made on compression moulded plaques



18R430

Processing guidelines

For Extrusion coating:

18R430 can be processed on commercial extrusion coating equipments over the melt temperature range 280 - 325 °C.

For Injection Moulding:

18R430 can be injected over the usual melt temperature range 190 - 250°C depending on part thickness, with high injection speeds in a cold mould regulated with water cooled usually at 14°C between 10 to 20°C.

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration.
It is advised to process the product within maximum one year after delivery.