



BPD2167

Product Technical Information

BPD2167 is an unstabilised low density thermoplastic polyethylene. It is designed for use in "Câble de façade" application and one step silane crosslinking insulation.

A carefully selected carbon black and additives master batch needs to be added to BPD2167 to reach the final "Cable de Façade" formulation. The best performance in terms of homogeneity, aging and anchorage tests is however obtained with the fully formulated black compound BPD8167, to which only the Silane mixture needs to be added.

Packaging

BPD2167 is sold in pellet form and is available in the following packaging: 25kg bags, 1.1 ton Holbins and bulk tankers.

Properties:

Properties	Test Method	Value	Units
Physical			
Melt flow rate	ISO 1133-1	0.2	g/10min
Conventional density	ISO 1183-1 & ISO 1872-1	930	kg/m ³
Tensile strength @ break	IEC 811-1-1	18	MPa
Elongation @ break	IEC 811-1-1	>500	%
Electrical			
Dielectric constant @ 50 Hz	ASTM D 150-2.2	2.3	
Dissipation factor @ 50 Hz	ASTM D 150	400	μrad
DC volume resistivity @ 23°C	ASTM D 257	10 ¹⁶	Ωcm
Dielectric strength, short time	ASTM D 149	>22	kV/mm

* Test on moulded crosslinked plaques prepared according to MTP 2006. Data should not be used for specification work