

Recycl-IN rHD5603



DATA SHEET

Product Technical Information

High density polyethylene resin containing 50% weight of post-consumer recyclate.

Benefits & Features

Recycl-IN rHD5603 is a pearl, ready to use high density polyethylene grade containing 50% post-consumer recyclate and supplied in pellet form. It has an outstanding stiffness and good environmental stress crack resistance (ESCR) balance making it ideal for use in a wide range of blow moulding applications.

- / High rigidity
- / Good environmental stress cracking resistance
- / High impact strength
- / Easy processing

Applications

- / Blow moulded containers up to 10 litres capacity for packaging chemicals, many household products and oils.
- / Sheet extrusion

This grade is not suitable for food packaging or pharma/medical applications

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

Recycl-IN rHD5603



Properties	Conditions	Test Methods	Values	Units
Physical				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	0.3	g/10min
Density		ISO 1183-1 & ISO 17855-1	956	kg/m ³
Mechanical				
Tensile Strength at Yield	23°C, Type 1 BA	ISO 527-2	32	MPa
Elongation at break	23°C, Type 1 BA	ISO 527-2	700	%
Flexural Modulus	23°C	ISO 178	1350	MPa
Notched Charpy Impact Strength	23°C	ISO 179	9	kJ/m ²
FNCT	50°C, 2% Arkopal N100, 5MPa	ISO 16770	25	hours
BTT stress crack resistance	F50 at 50°C, 100% concentration	ASTM D 1693	>90	hours

Data should not be used for specification work