



# M24N430

## Product Technical Information

Ethylene-MethAcrylic-Acid-Copolymer (EMAA) for extrusion coating.

## Benefits & Features

**M24N430** is an additive free ethylene-methacrylic-acid-copolymer (EMAA) with a medium MAA content. Its special polymer structure gives the following properties:

- Improved adhesion properties to standard LDPE/mLLDPE or other polar substrates, especially with aluminium foil and metallised film at high line speeds or low coating weights
- Good processability in mono- and coextrusion with comparable neck in and draw down to LDPE
- Exhibits very good sealing properties enhanced by the presence of the comonomer
- Good organoleptical properties
- Low fumes during processing, high purity and a low gel level

## Applications

**M24N430** is a speciality extrusion coating resin with improved adhesion characteristics. Main application fields include aluminium foil and metallised film both for industrial use, food and flexible packaging.

We recommend that you consult your INEOS technical representative for further advice on the use of **M24N430**.

Properties	Conditions	Test Methods	Values	Units
<b>Physical</b>				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	7.5	g/10 min
<b>Co-monomer</b>				
Methacrylic Acid Content		INEOS Test Method	3.7	%
<b>Thermal</b>				
Vicat Softening Temperature	Method A50 (10N, 50°C/h)	ISO306	90	°C
Melting Temperature	DSC, 10°C/min	INEOS Test Method	105	°C
<b>Data should not be used for specification work</b>				

## Processing guidelines

**M24N430** can be processed on commercial extrusion coating equipment over the melt temperature range from 260 to 320°C. Low coating weights can be obtained at extrusion rates normally used for common substrates.

Identical extrusion and processing parameters should be used as for conventional LDPE of identical MFR.

When extruding **M24N430** precautions should be taken to prevent equipment corrosion. The resin should not be left standing in the extruder for extended periods.

After extrusion of **M24N430**, the extruder should be purged with standard LDPE.

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C.

Exposure to direct sunlight should be avoided as this may lead to product deterioration.

It is advised to process the product within maximum one year after delivery.