

Diamond ABS 3501 GF30 9965WHI

LyondellBasell Industries - Acrylonitrile Butadiene Styrene

General Information

Product Description

Diamond ABS 3501 GF30 9965WHI is a Acrylonitrile Butadiene Styrene Glass Fiber, 30% filled material. Features include: High Impact Resistance.

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• High Impact Resistance
Forms	• Pellets

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.24		ASTM D792
Melt Mass-Flow Rate (MFR) ²			ASTM D1238
200°C/5.0 kg	0.10	g/10 min	
230°C/3.8 kg	3.0	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (Yield)	11400	psi	ASTM D638
Flexural Modulus ⁴	817000	psi	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.2	ft-lb/in	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Annealed, 0.125 in	217	°F	
Vicat Softening Temperature	239	°F	ASTM D1525 ⁵

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176 to 185	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	374 to 482	°F
Middle Temperature	374 to 482	°F
Front Temperature	374 to 482	°F
Mold Temperature	104 to 176	°F
Injection Rate	Moderate-Fast	