

Diamond ABS 7600B-1002

LyondellBasell Industries - Acrylonitrile Butadiene Styrene

General Information

Product Description

Diamond ABS 7600B-1002 is a Acrylonitrile Butadiene Styrene material and is typically used in Blow Molding applications. Features include: Ultra High Impact Resistance.

General

Features	<ul style="list-style-type: none"> Ultra High Impact Resistance
Processing Method	<ul style="list-style-type: none"> Blow Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) ²			ASTM D1238
200°C/5.0 kg	0.60	g/10 min	
230°C/3.8 kg	2.7	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (Yield)	5730	psi	ASTM D638
Flexural Modulus - Tangent ⁴	292000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	8.1	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.125 in	171	°F	
Deflection Temperature Under Load			ASTM D648
264 psi, Annealed, 0.125 in	201	°F	
Vicat Softening Temperature	219	°F	ASTM D1525 ⁵
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176 to 185	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	374 to 482	°F
Middle Temperature	374 to 482	°F
Front Temperature	374 to 482	°F
Mold Temperature	104 to 176	°F
Injection Rate	Moderate-Fast	