

Diamond ABS 7501 3448 BLACK

LyondellBasell Industries - Acrylonitrile Butadiene Styrene

General Information

Product Description

Diamond ABS 7501 3448 Black is a Acrylonitrile Butadiene Styrene material and is typically used in Injection Molding applications. Features include: Ultra High Impact Resistance.

General

Features	<ul style="list-style-type: none"> • Ultra High Impact Resistance
Forms	<ul style="list-style-type: none"> • Pellets
Processing Method	<ul style="list-style-type: none"> • Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.04		ASTM D792
Melt Mass-Flow Rate (MFR) ² (230°C/3.8 kg)	3.6	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (Yield)	6190	psi	ASTM D638
Flexural Modulus - Tangent ⁴	286000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	7.5	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	101		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed, 0.125 in	171	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Annealed, 0.125 in	199	°F	ASTM D648
Vicat Softening Temperature	217	°F	ASTM D1525 ⁵
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176 to 185	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	374 to 482	°F
Middle Temperature	374 to 482	°F
Front Temperature	374 to 482	°F
Mold Temperature	104 to 176	°F
Injection Rate	Moderate-Fast	