



# Polyflam RABS 90000 UV5 L WHI1-1934H

LyondellBasell Industries - Acrylonitrile Butadiene Styrene

## General Information

### Product Description

ABS Flame Retardant

### General

Additive	• Flame Retardant
Features	• Flame Retardant
Processing Method	• Injection Molding
Resin ID	• ABS FR17

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm <sup>3</sup>	ISO 1183/A
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	319000	psi	ISO 527-1/1A/1
Tensile Stress (Yield, 73°F)	6090	psi	ISO 527-2/1A/50
Tensile Strain (Break, 73°F)	3.0	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.8	ft·lb/in <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	176	°F	ISO 75-2/Ae
Vicat Softening Temperature	221	°F	ISO 306/A50