

# Starex HF-0670 U

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

## General Information

### General

RoHS Compliance • RoHS Compliant

### Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.04		ASTM D792
Density (Natural)	1.04	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.5	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.5	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.30 to 0.60	%	
Flow : 0.0787 in	0.30 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	284000	psi	ASTM D638
Tensile Modulus	334000	psi	ISO 527-1/50
Tensile Strength <sup>2</sup> (Yield)	5400	psi	ASTM D638
Tensile Stress (Yield)	6090	psi	ISO 527-2/50
Tensile Strength <sup>2</sup> (Break)	4840	psi	ASTM D638
Tensile Stress (Break)	4790	psi	ISO 527-2/50
Flexural Modulus <sup>3</sup>	313000	psi	ASTM D790
Flexural Modulus <sup>4</sup>	348000	psi	ISO 178
Flexural Strength <sup>3</sup>	8530	psi	ASTM D790
Flexural Stress <sup>4</sup>	10000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup> (73°F)	10	ft-lb/in <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	4.0	ft-lb/in	
73°F, 0.250 in	3.7	ft-lb/in	
Notched Izod Impact Strength <sup>5</sup> (73°F)	8.6	ft-lb/in <sup>2</sup>	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	107		ASTM D785
Rockwell Hardness (R-Scale)	109		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.252 in	183	°F	
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed, 0.157 in	169	°F	
Vicat Softening Temperature	201 198	°F	ISO 306/B50

## Starex HF-0670 U

### Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

#### Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	176	°F
Hot Air Dryer	176	°F
Drying Time		
Desiccant Dryer	2.0 to 3.0	hr
Hot Air Dryer	2.0 to 4.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	320 to 356	°F
Middle Temperature	374 to 392	°F
Front Temperature	410 to 428	°F
Nozzle Temperature	446	°F
Mold Temperature	104 to 176	°F
Injection Pressure	7110 to 21300	psi
Back Pressure	71.1 to 284	psi
Screw Speed	50 to 150	rpm

#### Injection Notes

Hot Runner Temperature: 230 °C