

# Starex LH-0300

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

## General Information

### General

Uses • Automotive Applications

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.04		ASTM D792
Density (Natural)	1.04	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	10	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	10	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.40 to 0.70	%	
Flow : 0.0787 in	0.40 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	251000	psi	ASTM D638
Tensile Modulus	274000	psi	ISO 527-1/50
Tensile Strength <sup>2</sup> (Yield)	5040	psi	ASTM D638
Tensile Stress (Yield)	5220	psi	ISO 527-2/50
Tensile Strength <sup>2</sup> (Break)	4710	psi	ASTM D638
Tensile Stress (Break)	4930	psi	ISO 527-2/50
Tensile Elongation <sup>2</sup> (Break)	51	%	ASTM D638
Tensile Strain (Break)	60	%	ISO 527-2/50
Flexural Modulus <sup>3</sup>	250000	psi	ASTM D790
Flexural Modulus <sup>4</sup>	299000	psi	ISO 178
Flexural Strength <sup>3</sup>	6610	psi	ASTM D790
Flexural Stress <sup>4</sup>	8410	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup> (73°F)	7.6	ft-lb/in <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	2.8	ft-lb/in	
73°F, 0.250 in	1.8	ft-lb/in	
Notched Izod Impact Strength <sup>5</sup> (73°F)	8.1	ft-lb/in <sup>2</sup>	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Rockwell Hardness (R-Scale)	100		ISO 2039-2

## Starex LH-0300

### Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 66 psi, Unannealed, 0.252 in	210	°F	ASTM D648
Deflection Temperature Under Load 66 psi, Unannealed, 0.157 in	201	°F	ISO 75-2/B
Deflection Temperature Under Load 66 psi, Annealed, 0.157 in	217	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed, 0.252 in	190	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed, 0.157 in	176	°F	ISO 75-2/A
Deflection Temperature Under Load 264 psi, Annealed, 0.157 in	212	°F	ISO 75-2/A
Vicat Softening Temperature	212	°F	ISO 306/B50

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	176	°F
Hot Air Dryer	176	°F
Drying Time		
Desiccant Dryer	2.0 to 3.0	hr
Hot Air Dryer	3.0 to 4.0	hr
Suggested Max Moisture	< 0.10	%
Rear Temperature	356 to 392	°F
Middle Temperature	392 to 428	°F
Front Temperature	410 to 446	°F
Nozzle Temperature	428 to 482	°F
Mold Temperature	104 to 176	°F
Injection Pressure	7110 to 21300	psi
Back Pressure	71.1 to 284	psi
Screw Speed	50 to 100	rpm

### Injection Notes

Hot Runner Temperature: 230 to 250°C