

Starex SR-0320LI

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.05		ASTM D792
Density (Natural)	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.40 to 0.70	%	
Flow : 0.0787 in	0.40 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	5690	psi	ASTM D638
Tensile Stress (Yield)	6530	psi	ISO 527-2/50
Tensile Strength ² (Break)	5550	psi	ASTM D638
Tensile Stress (Break)	6090	psi	ISO 527-2/50
Flexural Modulus ³	284000	psi	ASTM D790
Flexural Modulus ⁴	348000	psi	ISO 178
Flexural Strength ³	8680	psi	ASTM D790
Flexural Stress ⁴	10700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (73°F)	11	ft·lb/in ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	4.4	ft·lb/in	
73°F, 0.250 in	4.0	ft·lb/in	
Notched Izod Impact Strength ⁵ (73°F)	11	ft·lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Rockwell Hardness (R-Scale)	110		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.252 in	203	°F	
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed, 0.157 in	187	°F	
Vicat Softening Temperature	225	°F	ISO 306/B50

Starex SR-0320LI

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	176 to 194	°F
Hot Air Dryer	176 to 194	°F
Drying Time		
Desiccant Dryer	4.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	< 0.10	%
Rear Temperature	392 to 428	°F
Middle Temperature	428 to 464	°F
Front Temperature	464 to 500	°F
Nozzle Temperature	464 to 500	°F
Mold Temperature	140 to 176	°F
Injection Pressure	11400 to 21300	psi
Back Pressure	71.1 to 284	psi
Screw Speed	50 to 150	rpm

Injection Notes

Hot Runner Temperature: 240 to 270 °C