

Starex SR-0325

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

General Information

General

Uses • Automotive Applications

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.06		ASTM D792
Density (Natural)	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.5	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.5	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	334000	psi	ASTM D638
Tensile Modulus	363000	psi	ISO 527-1/50
Tensile Strength ² (Yield)	7110	psi	ASTM D638
Tensile Stress (Yield)	7250	psi	ISO 527-2/50
Tensile Strength ² (Break)	6540	psi	ASTM D638
Tensile Stress (Break)	6530	psi	ISO 527-2/50
Tensile Elongation ² (Break)	20	%	ASTM D638
Tensile Strain (Break)	20	%	ISO 527-2/50
Flexural Modulus ³	363000	psi	ASTM D790
Flexural Modulus ⁴	363000	psi	ISO 178
Flexural Strength ³	10700	psi	ASTM D790
Flexural Stress ⁴	10600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (73°F)	5.7	ft·lb/in ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	2.8	ft·lb/in	
73°F, 0.250 in	2.2	ft·lb/in	
Notched Izod Impact Strength ⁵ (73°F)	5.7	ft·lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Rockwell Hardness (R-Scale)	115		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.252 in	217	°F	
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed, 0.157 in	198	°F	
Vicat Softening Temperature	239	°F	ISO 306/B50

Starex SR-0325

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	176 to 194	°F
Hot Air Dryer	176 to 194	°F
Drying Time		
Desiccant Dryer	3.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	< 0.10	%
Rear Temperature	374 to 428	°F
Middle Temperature	410 to 446	°F
Front Temperature	446 to 500	°F
Nozzle Temperature	446 to 500	°F
Mold Temperature	104 to 176	°F
Injection Pressure	7110 to 21300	psi
Back Pressure	711 to 2130	psi
Screw Speed	5 to 20	rpm

Injection Notes

Hot Runner Temperature: 230 to 260°C