

# Starex NH-0927

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

## General Information

General	
Additive	<ul style="list-style-type: none"> <li>Flame Retardant</li> </ul>
Features	<ul style="list-style-type: none"> <li>Flame Retardant</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Electrical/Electronic Applications</li> </ul>

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.05		ASTM D792
Density (Natural)	1.06	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.5	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.6	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage - Flow (0.0787 in)	0.30 to 0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	334000	psi	ASTM D638
Tensile Modulus	363000	psi	ISO 527-1/50
Tensile Strength <sup>2</sup> (Yield)	7820	psi	ASTM D638
Tensile Stress (Yield)	7250	psi	ISO 527-2/50
Tensile Strength <sup>2</sup> (Break)	5120	psi	ASTM D638
Tensile Stress (Break)	5220	psi	ISO 527-2/50
Tensile Elongation <sup>2</sup> (Break)	25	%	ASTM D638
Tensile Strain (Break)	13	%	ISO 527-2/50
Flexural Modulus <sup>3</sup>	377000	psi	ASTM D790
Flexural Modulus <sup>4</sup>	377000	psi	ISO 178
Flexural Strength <sup>3</sup>	9530	psi	ASTM D790
Flexural Stress <sup>4</sup>	11300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup> (73°F)	10	ft·lb/in <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	3.4	ft·lb/in	
73°F, 0.250 in	3.0	ft·lb/in	
Notched Izod Impact Strength <sup>5</sup> (73°F)	10	ft·lb/in <sup>2</sup>	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Rockwell Hardness (R-Scale)	112		ISO 2039-2

## Starex NH-0927

### Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 66 psi, Unannealed, 0.252 in	201	°F	ASTM D648
Deflection Temperature Under Load 66 psi, Unannealed, 0.157 in	194	°F	ISO 75-2/B
Deflection Temperature Under Load 66 psi, Annealed, 0.157 in	185	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed, 0.252 in	190	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed, 0.157 in	172	°F	ISO 75-2/A
Deflection Temperature Under Load 264 psi, Annealed, 0.157 in	192	°F	ISO 75-2/A
Vicat Softening Temperature --	210	°F	ISO 306/B120
--	205	°F	ISO 306/B50

Flammability	Nominal Value	Unit	Test Method
Flame Rating 0.04 in	V-2		UL 94
0.12 in	V-2		

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	176	°F
Hot Air Dryer	176	°F
Drying Time		
Desiccant Dryer	2.0 to 3.0	hr
Hot Air Dryer	2.0 to 4.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	320 to 356	°F
Middle Temperature	374 to 392	°F
Front Temperature	410 to 428	°F
Nozzle Temperature	446	°F
Mold Temperature	104 to 176	°F
Injection Pressure	7110 to 21300	psi
Back Pressure	71.1 to 284	psi
Screw Speed	50 to 150	rpm

#### Injection Notes

Hot Runner Temperature: 230°C