

Starex MP-0670

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

General Information

General

Features	<ul style="list-style-type: none"> • Platable
Uses	<ul style="list-style-type: none"> • Automotive Applications

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.04		ASTM D792
Density (Natural)	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.3	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.3	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.30 to 0.60	%	
Flow : 0.0787 in	0.30 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	307000	psi	ASTM D638
Tensile Modulus	319000	psi	ISO 527-1/50
Tensile Strength ² (Yield)	6400	psi	ASTM D638
Tensile Stress (Yield)	7400	psi	ISO 527-2/50
Flexural Modulus ³	306000	psi	ASTM D790
Flexural Modulus ⁴	341000	psi	ISO 178
Flexural Strength ³	9390	psi	ASTM D790
Flexural Stress ⁴	10400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (73°F)	12	ft·lb/in ²	ISO 179/1eA
Notched Izod Impact (73°F, 0.250 in)	4.4	ft·lb/in	ASTM D256
Notched Izod Impact Strength ⁵ (73°F)	13	ft·lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Rockwell Hardness (R-Scale)	108		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	208	°F	ISO 306/B50

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	185 to 203	°F
Hot Air Dryer	185 to 203	°F
Drying Time		
Desiccant Dryer	2.0 to 4.0	hr
Hot Air Dryer	2.0 to 4.0	hr

Starex MP-0670

Lotte Chemical Corporation - Acrylonitrile Butadiene Styrene

Injection	Nominal Value	Unit
Suggested Max Moisture	< 0.10	%
Rear Temperature	356 to 392	°F
Middle Temperature	392 to 410	°F
Front Temperature	410 to 446	°F
Nozzle Temperature	428 to 464	°F
Mold Temperature	104 to 176	°F
Injection Pressure	7110 to 21300	psi
Back Pressure	71.1 to 284	psi
Screw Speed	50 to 150	rpm

Injection Notes

Hot Runner Temperature: 210 to 230 °C