



Toyolac™ 335 X01

Toray Industries, Inc. - Acrylonitrile Butadiene Styrene

General Information

Product Description

Good appearance

General

Features	• Pleasing Surface Appearance
Uses	<ul style="list-style-type: none"> • Automotive Applications • Automotive Exterior Parts • Automotive Interior Parts • Consumer Applications • Electrical Housing • Electrical/Electronic Applications • Kitchenware • White Goods & Small Appliances
Processing Method	• Injection Molding
ISO Designation	• >ABS<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	24	g/10 min	ISO 1133
Molding Shrinkage ²	0.40 to 0.70	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (73°F)	6380	psi	ISO 527-2
Tensile Strain (Break, 73°F)	6.0	%	ISO 527-2
Flexural Modulus (73°F)	338000	psi	ISO 178
Flexural Stress (73°F)	9720	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	15	ft·lb/in ²	ISO 179
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	112		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	181	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.

² 23°C/50%RH