

Microthene MU76000

LyondellBasell Industries - Ethylene Vinyl Acetate Copolymer

General Information

Product Description

Microthene G polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. Microthene G powders combine the unique properties of a polyolefin resin with a small ground particle size.

General

Uses	<ul style="list-style-type: none"> Automotive Applications Automotive Interior Parts Color Concentrates 	<ul style="list-style-type: none"> Construction Applications Consumer Applications Flexible Packaging 	<ul style="list-style-type: none"> Industrial Applications Medical/Healthcare Applications Structural Parts
Forms	<ul style="list-style-type: none"> Powder 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (23°F)	0.941	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) ²	32	g/10 min	ASTM D1238
Vinyl Acetate Content	18.0	wt%	Internal Method
Average Particle Size	35	mesh	Internal Method
Particle Shape	Irregular		Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	1360	psi	ASTM D638
Tensile Elongation (Break)	760	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	30		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -105	°F	ASTM D746
Vicat Softening Temperature	129	°F	ASTM D1525
Peak Melting Temperature	185	°F	ASTM D3418