



Centrex ASA 814 90203 UVWHI

LyondellBasell Industries - Acrylonitrile Styrene Acrylate

General Information

Product Description

Centrex ASA 814 90203 UVWHI is a Acrylonitrile Styrene Acrylate material and is typically used in Injection Molding applications. Features include: Good Processability, Good Weather Resistance, High Gloss, High Impact Resistance, and UV Resistant.

General

Features	<ul style="list-style-type: none"> • Good Processability • Good Weather Resistance 	<ul style="list-style-type: none"> • High Gloss • High Impact Resistance 	<ul style="list-style-type: none"> • UV Resistant
Uses	<ul style="list-style-type: none"> • Decorative Displays • Electronic Displays • Lawn & Garden Equipment 	<ul style="list-style-type: none"> • Marine Applications • Outdoor Applications • Spas 	<ul style="list-style-type: none"> • Sporting Goods • Water Sports Equipment
Forms	<ul style="list-style-type: none"> • Pellets 		
Processing Method	<ul style="list-style-type: none"> • Injection Molding 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.05		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/10.0 kg)	9.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (0.201 in)	305000	psi	ASTM D638
Tensile Strength ² (Yield)	5600	psi	ASTM D638
Flexural Modulus - Tangent ³	325000	psi	ASTM D790
Flexural Strength ³	9950	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-22°F, 0.125 in	1.4	ft-lb/in	
73°F, 0.125 in	5.1	ft-lb/in	
Instrumented Dart Impact			ASTM D3763
-22°F	72.6	in-lb	
73°F	292	in-lb	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	101		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.125 in	160	°F	
264 psi, Unannealed, 0.250 in	170	°F	
RTI Elec (0.06 in)	122	°F	UL 746B
RTI Imp (0.06 in)	122	°F	UL 746B
RTI Str (0.06 in)	122	°F	UL 746B
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180 to 190	°F
Drying Time	2.0	hr

Centrex ASA 814 90203 UVWHI
LyondellBasell Industries - Acrylonitrile Styrene Acrylate

Injection	Nominal Value	Unit
Suggested Max Moisture	0.10	%
Suggested Shot Size	50 to 70	%
Rear Temperature	460 to 520	°F
Middle Temperature	460 to 520	°F
Front Temperature	460 to 520	°F
Nozzle Temperature	460 to 520	°F
Processing (Melt) Temp	460 to 520	°F
Mold Temperature	109 to 180	°F
Injection Rate	Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.20 in/min

³ 0.051 in/min