

# Starex WX-9310UV

Lotte Chemical Corporation - Acrylonitrile Styrene Acrylate

## General Information

### General

Uses • Automotive Applications

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.08		ASTM D792
Density (Natural)	1.08	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.40 to 0.70	%	
Flow : 0.0787 in	0.40 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	277000	psi	ASTM D638
Tensile Modulus	319000	psi	ISO 527-1/50
Tensile Strength <sup>2</sup> (Yield)	6260	psi	ASTM D638
Tensile Stress (Yield)	7110	psi	ISO 527-2/50
Tensile Strength <sup>2</sup> (Break)	5260	psi	ASTM D638
Tensile Stress (Break)	5370	psi	ISO 527-2/50
Tensile Elongation <sup>2</sup> (Break)	12	%	ASTM D638
Tensile Strain (Break)	12	%	ISO 527-2/50
Flexural Modulus <sup>3</sup>	313000	psi	ASTM D790
Flexural Modulus <sup>4</sup>	348000	psi	ISO 178
Flexural Strength <sup>3</sup>	9670	psi	ASTM D790
Flexural Stress <sup>4</sup>	10200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup> (73°F)	6.7	ft·lb/in <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	3.4	ft·lb/in	
73°F, 0.250 in	1.6	ft·lb/in	
Notched Izod Impact Strength <sup>5</sup> (73°F)	7.6	ft·lb/in <sup>2</sup>	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Rockwell Hardness (R-Scale)	106		ISO 2039-2

## Starex WX-9310UV

### Lotte Chemical Corporation - Acrylonitrile Styrene Acrylate

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 66 psi, Unannealed, 0.252 in	207	°F	ASTM D648
Deflection Temperature Under Load 66 psi, Unannealed, 0.157 in	205	°F	ISO 75-2/B
Deflection Temperature Under Load 66 psi, Annealed, 0.157 in	223	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed, 0.252 in	194	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed, 0.157 in	176	°F	ISO 75-2/A
Deflection Temperature Under Load 264 psi, Annealed, 0.157 in	216	°F	ISO 75-2/A
Vicat Softening Temperature --	217	°F	ISO 306/B120
--	214	°F	ISO 306/B50

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature Desiccant Dryer	167 to 185	°F
Hot Air Dryer	167 to 185	°F
Drying Time Desiccant Dryer	2.0 to 4.0	hr
Hot Air Dryer	2.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	374 to 401	°F
Middle Temperature	401 to 437	°F
Front Temperature	437 to 473	°F
Nozzle Temperature	473	°F
Mold Temperature	122 to 158	°F
Injection Pressure	14200	psi
Back Pressure	142 to 284	psi
Screw Speed	50 to 90	rpm

#### Injection Notes

Hot Runner Temperature: 230 to 260°C

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.20 in/min

<sup>3</sup> 0.11 in/min

<sup>4</sup> 0.079 in/min

<sup>5</sup> 4mm