

LAPEROS® S140M

Polyplastics - Liquid Crystal Polymer

General Information

Product Description

High Heat Resistance, High-temperature Stiffness

GF Reinforced, High Flow

General

Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• High Flow • High Heat Resistance • High Stiffness
UL File Number	• E106764
Part Marking Code (ISO 11469)	• >LCP-GF40<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.70	g/cm ³	ISO 1183
Molding Shrinkage ²			Internal Method
Across Flow : 0.0394 in	0.76	%	
Flow : 0.0394 in	0.12	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17400	psi	ASTM D638
Tensile Elongation (Break)	2.1	%	ASTM D638
Flexural Modulus	1.87E+6	psi	ISO 178
Flexural Stress	27600	psi	ISO 178
Flexural Strain	2.8	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.3	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	85		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	590	°F	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
0.0394 in	940	V/mil	
0.118 in	460	V/mil	
Relative Permittivity			IEC 60250
1 kHz	4.00		
1 MHz	3.80		
Dissipation Factor			IEC 60250
1 kHz	0.010		
1 MHz	0.010		
Arc Resistance	154	sec	ASTM D495

LAPEROS® S140M

Polyplastics - Liquid Crystal Polymer

Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	
Color Number	VF2001/BK010P		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 80x80x1 mm, 60 MPa Injection Pressure