



Polyaxis LP 8000-1684G WHITEWHI

LyondellBasell Industries - Metallocene High Density Polyethylene

General Information

Product Description

Polyaxis LP-8000 is a high density polyethylene intended for the rotational molding industry. This stiff yet tough compound has been used in watercraft with good success.

General

Additive	• Long Term UV-10 Stabilizer
Features	• UV Stabilized
Appearance	• Colors Available
Forms	• Pellets • Powder
Processing Method	• Rotational Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.947		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.6	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 10% Igepal, Compression Molded, F50	6.00	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, Rotational Molded)	3210	psi	ASTM D638
Tensile Elongation ² (Break, Rotational Molded)	500	%	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	145000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Impact Strength			ARM
-40°F, 0.125 in, Rotational Molded	65	ft-lb	
-40°F, 0.250 in, Rotational Molded	> 190	ft-lb	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 66 psi, Unannealed, 0.125 in, Rotational Molded	160	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed, 0.125 in, Rotational Molded	103	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min