HK:+852-69575415 China GuangDong:+13538586433 ShangHai:+18816996168

Polyaxis LP 8800-L01G

LyondellBasell Industries - Metallocene High Density Polyethylene

General Information

Product Description

Polyaxis LP-8800 is a high density polyethylene intended for the rotational molding industry. This stiff yet tough compound was designed for watercraft products.

General

Additive	• UV Stabilizer	
Features	• UV Stabilized	
Appearance	• Colors Available	
Forms	• Pellets	• Powder
Processing Method	• Rotational Molding	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.955		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.2	g/10 min	ASTM D1238
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength [2] (Yield, Rotational Molded)	3630	psi	ASTM D638
Tensile Elongation (Yield)	9.0	%	ASTM D638
Tensile Elongation [2] (Break, Rotational Molded)	270	%	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	162000	psi	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Impact Strength (39°F, 0.126 in, Rotational Molded)	61	ft·lb	ARM

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] 2.0 in/min