

Icorene 3940-4A550G PEB BEACH GRANI

LyondellBasell Industries - Linear Low Density Polyethylene

General Information

Product Description

Icorene 3940-4A550G PEB BEACH GRANI is a linear low density polyethylene developed for rotational molding applications. The resin is UV stabilized and suitable for general purpose applications. It has a good balance of properties such as toughness and stiffness.

General

Uses	<ul style="list-style-type: none"> Containers Drums 	<ul style="list-style-type: none"> Outdoor Applications Rigid Packaging 	<ul style="list-style-type: none"> Sporting Goods Toys
Processing Method	<ul style="list-style-type: none"> Rotational Molding 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (23°F)	0.940	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.6	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 100% Igepal, F50	> 1000	hr	ASTM D1693A
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	2900	psi	ASTM D638
Flexural Modulus			ASTM D790
1% Secant	119000	psi	
2% Secant	102000	psi	
Impact	Nominal Value	Unit	Test Method
Impact Strength			ARM
-40°F, 0.125 in	54	ft·lb	
-40°F, 0.250 in	160	ft·lb	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	136	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	104	°F	ASTM D648