

Microthene PE-LD150

LyondellBasell Industries - Low Density Polyethylene

General Information

Product Description

PE-LD150 are use in a broad range of specialty applications. PE-LD150 powders combine the unique properties of a polyolefin resin with a small particle size.

General

| | | |
|------------|---|---|
| Uses | <ul style="list-style-type: none"> Automotive Applications Color Concentrates | <ul style="list-style-type: none"> Industrial Applications Structural Parts |
| Appearance | <ul style="list-style-type: none"> Natural Color | |
| Forms | <ul style="list-style-type: none"> Powder | |

Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|-------------------|-----------------|
| Density | 0.923 | g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 5.2 | g/10 min | ASTM D1238 |
| Moisture Content | < 0.10 | % | Internal Method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 1800 | psi | ASTM D638 |
| Tensile Elongation (Break) | 550 | % | ASTM D638 |
| Flexural Modulus | 40000 | psi | ASTM D790 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 53 | | ASTM D2240 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | < -105 | °F | ASTM D746 |
| Vicat Softening Temperature | 207 | °F | ASTM D1525 |
| Peak Melting Temperature | 230 | °F | ASTM D3418 |