

Polyaxis CP 812 101 WHITE PELLETS

LyondellBasell Industries - Linear Low Density Polyethylene

General Information

Product Description

Polyaxis CP 812 is a general purpose linear low density polyethylene compound offering quick cycles and part to part consistency. Available as pellet or powder.

General

Additive	• Long Term UV-8 Stabilizer	
Features	• Fast Molding Cycle	• UV Stabilized
Uses	• General Purpose	
Appearance	• Colors Available	
Forms	• Pellets	• Powder
Processing Method	• Rotational Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.932 to 0.939	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0 to 7.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
10% Igepal, Compression Molded, F50	> 25.0	hr	
100% Igepal, Compression Molded, F50	> 500	hr	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, Rotational Molded)	2250	psi	ASTM D638
Tensile Elongation ² (Break, Rotational Molded)	500	%	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	85000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Impact Strength			ARM
-40°F, 0.125 in, Rotational Molded	56	ft-lb	
-40°F, 0.250 in, Rotational Molded	145	ft-lb	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi, Unannealed, 0.0492 in, Rotational Molded	129	°F	
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.0492 in, Rotational Molded	96.8	°F	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min