



# Amilan™ CM1017-K

Toray Industries, Inc. - Polyamide 6

## General Information

### Product Description

High rigidity

### General

Features	<ul style="list-style-type: none"> <li>Chemical Resistant</li> </ul>		
Uses	<ul style="list-style-type: none"> <li>Appliance Components</li> <li>Automotive Applications</li> <li>Automotive Electronics</li> </ul>	<ul style="list-style-type: none"> <li>Connectors</li> <li>Construction Applications</li> <li>Electrical/Electronic Applications</li> </ul>	<ul style="list-style-type: none"> <li>Office Automation Equipment</li> <li>Sporting Goods</li> <li>White Goods &amp; Small Appliances</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>		
ISO Designation	<ul style="list-style-type: none"> <li>&gt;PA6&lt;</li> </ul>		

## Properties<sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density (73°F)	1.13	--	g/cm <sup>3</sup>	ISO 1183
Spiral Flow <sup>2</sup>	26.4	--	in	Internal Method
Molding Shrinkage				Internal Method
0.0394 in <sup>3</sup>	0.50 to 1.0	--	%	
0.118 in <sup>4</sup>	1.0 to 1.6	--	%	
Water Absorption <sup>5</sup> (24 hr, 73°F)	1.8	--	%	ISO 62
Water Absorption <sup>5</sup>				ISO 62
Saturation, 73°F	11	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (73°F)	13100	6530	psi	ISO 527-2
Tensile Strain (Break, 73°F)	25	> 50	%	ISO 527-2
Flexural Modulus (73°F)	450000	160000	psi	ISO 178
Flexural Stress (73°F)	17400	7250	psi	ISO 178
Compressive Stress (73°F)	12300	--	psi	ISO 604
Shear Strength (73°F)	10900	10200	psi	ASTM D732
Taber Abrasion Resistance				ISO 9352
1000 Cycles	3.00 to 4.00	--	mg	
Coefficient of Friction - vs. Metal <sup>6</sup>	0.15 to 0.20	--		Suzuki Method
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°F	1.2	--	ft·lb/in <sup>2</sup>	
73°F	1.7	15	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179
-40°F	No Break	--		
73°F	No Break	--		
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ISO 2039-2
R-Scale, 73°F	119	90		
R-Scale, 176°F	80	--		

**Amilan™ CM1017-K**  
**Toray Industries, Inc. - Polyamide 6**

<b>Thermal</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load 66 psi, Unannealed	381	--	°F	ISO 75-2/B
Melting Temperature	437	--	°F	DSC
Specific Heat	0.454	--	Btu/lb/°F	
Thermal Conductivity	1.7	--	Btu·in/hr/ft <sup>2</sup> /°F	
Coefficient of Linear Thermal Expansion	8	--	cm <sup>-5</sup> /cm/°C	ISO 11359-2
<b>Electrical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Volume Resistivity	1.0E+14 to 1.0E+15	1.0E+11 to 1.0E+12	ohms·cm	IEC 60093
Electric Strength	510	--	V/mil	IEC 60243-1
Dielectric Constant				IEC 60250
73°F, 50 Hz	4.10	9.00		
73°F, 1 kHz	3.90	8.00		
73°F, 1 MHz	3.40	4.50		
Dissipation Factor				IEC 60250
73°F, 50 Hz	0.070	0.10		
73°F, 1 kHz	0.060	0.11		
73°F, 1 MHz	0.030	0.13		
Arc Resistance	120	--	sec	UL 746
Comparative Tracking Index (CTI)	> 600	--	V	UL 746A
<b>Flammability</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating (0.06 in)	V-2	V-2		UL 94

**Additional Information**

Dry Water absorption Moisture Content 3.5%

**Notes**

- <sup>1</sup> Typical properties: these are not to be construed as specifications.
- <sup>2</sup> Melt Temperature: 500°F, Injection Pressure: 1.31E+4 psi, 0.0787 in
- <sup>3</sup> 80x80x1mm
- <sup>4</sup> 80x80x3mm
- <sup>5</sup> in water
- <sup>6</sup> Without Lubrication