

Radilon® MIXLOY S RVA80T 100 NT

Radici Group High Performance Polymers - Polyamide 6 + ABS

General Information

Product Description

PA6/ABS blend, 8% glass fibre injection moulding grade. Toughened. Natural colour.

Suitable for parts requiring improved stiffness, along with improved impact resistance. Excellent aesthetic surface aspect.

General

Filler / Reinforcement	• Glass Fiber, 8.0% Filler by Weight
Additive	• Impact Modifier
Features	• Good Impact Resistance • Impact Modified • Good Stiffness • Outstanding Surface Finish
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• (PA6+ABS)-I-GF8

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	5.3	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	1.7	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	580000	363000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	10900	7980	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	4.0	6.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	6.0	20	%	ISO 527-2/1A/50
Flexural Modulus ²	493000	326000	psi	ISO 178
Flexural Stress ²	17400	10900	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
73°F	5.5	--	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
73°F	29	36	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Vicat Softening Temperature	302	--	°F	ISO 306/B50
Melting Temperature ³	432	--	°F	ISO 11357-3

Radilon® MIXLOY S RVA80T 100 NT

Radici Group High Performance Polymers - Polyamide 6 + ABS

Processing Information

Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	464 to 500	°F
Mold Temperature	104 to 140	°F
Injection Rate	Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 10°C/min