

Radilon® MIXLOY S RVA80K 100 NT

Radici Group High Performance Polymers - Polyamide 6 + ABS

General Information

Product Description

PA6/ABS blend, 8% glass fibre injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring improved stiffness and low moisture absorption. Excellent aesthetic surface aspect.

General

Filler / Reinforcement	• Glass Fiber, 8.0% Filler by Weight
Features	• Good Stiffness • Low Moisture Absorption • Outstanding Surface Finish
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• (PA6+ABS)-GF8

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.60	%	
Flow	0.40	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	5.7	%	ISO 62
Water Absorption			ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	1.8	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	580000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	12300	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	4.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	5.8	%	ISO 527-2/1A/50
Flexural Modulus ²	537000	psi	ISO 178
Flexural Stress ²	20300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (73°F)	26	ft-lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ³	428	°F	ISO 11357-3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	464 to 500	°F
Mold Temperature	104 to 140	°F
Injection	Nominal Value	Unit
Injection Rate	Moderate	