

Radiflam® S RV300K AE 321 C BK

Radici Group High Performance Polymers - Polyamide 6

General Information

Product Description

PA6 flame retardant injection moulding grade. 30% glass fiber reinforced. Black colour.

Suitable for parts requiring fire retardancy, high stiffness and good mechanical resistance. Good electrical insulating properties. Rated V-0 according to UL-94.

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • High Stiffness
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GF30 FR(17+72)

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.62	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.50	--	%	
Flow	0.20	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	3.2	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	0.90	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.61E+6	--	psi	ISO 527-1/1A/1
Tensile Stress (Break)	17400	--	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.7	--	%	ISO 527-2/1A/5
Flexural Modulus ²	1.51E+6	--	psi	ISO 178
Flexural Stress ²	26100	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
73°F	3.8	--	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
73°F	15	--	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Af
264 psi, Unannealed	401	--	°F	
Vicat Softening Temperature	392	--	°F	ISO 306/B50
Ball Indentation Temperature	> 329	--	°F	IEC 60695-10-2
Melting Temperature ³	428	--	°F	ISO 11357-3

Radiflam® S RV300K AE 321 C BK Radici Group High Performance Polymers - Polyamide 6

Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
Comparative Tracking Index Solution A	350	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	V-0	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.04 in	1760	--	°F	
0.08 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.04 in	1560	--	°F	
0.08 in	1560	--	°F	

Processing Information

Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.10	%
Processing (Melt) Temp	482 to 536	°F
Mold Temperature	176 to 194	°F
Injection Rate	Moderate-Fast	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 10°C/min